



**AMENDMENTS TO THE CLAIMS:**

The following listing of claims replaces all prior listings, and all prior versions, of claims in the application.

**LISTING OF CLAIMS:**

1. and 2. (Cancelled).

3. (Previously presented) A lithium secondary battery having a positive electrode and a negative electrode which reversibly intercalate and deintercalate lithium, the negative electrode containing amorphous carbon, and an electrolyte containing an ion conductive material and an electrolytic salt, where the ion conductive material comprises a polymerizable composition which contains a boron-containing compound represented by the following formula (2) and a boron-containing compound represented by the following formula (3):



wherein B represents a boron atom;  $Z_4$ ,  $Z_5$  and  $Z_6$  each represent an organic group having an acryloyl group or a methacryloyl group or a hydrocarbon group of 1-10 carbon atoms, with the proviso that at least one of  $Z_4$ ,  $Z_5$  and  $Z_6$  is said organic group having an acryloyl group or a methacryloyl group;  $R_1$ ,  $R_2$  and  $R_3$  each represent a hydrocarbon group of 1-10 carbon atoms; AO represents an oxyalkylene group of 1-

6 carbon atoms; and each of p, q, r,  $\alpha$ ,  $\beta$  and  $\gamma$  is more than 0 and less than 4, provided that each of the sum  $p+q+r$  and the sum  $\alpha+\beta+\gamma$  is 1 or more.

4. (Previously presented) A lithium secondary battery according to claim 3, wherein the molar ratio of the compound of the formula (2) and the compound of the formula (3) [(molar number of the compound of the formula (3))/(molar number of the compound of the formula (2))] is 0.1 to 9.

5. (Original) A lithium secondary battery according to claim 3, wherein the electrolyte contains a polymer obtained by polymerizing the polymerizable composition.

6. (Original) A lithium secondary battery according to claim 4, wherein the electrolyte contains a polymer obtained by polymerizing the polymerizable composition.

7. and 8. (Cancelled).

9. (Original) A lithium secondary battery according to claim 3, wherein the electrolytic salt is at least one of  $\text{LiPF}_6$ ,  $\text{LiN}(\text{CF}_3 \text{ SO}_2)_2$ ,  $\text{LiClO}_4$ ,  $\text{LiBF}_4$ ,  $\text{LiAsF}_6$ ,  $\text{LiI}$ ,  $\text{LiBr}$ ,  $\text{LiSCN}$ ,  $\text{Li}_2\text{B}_{10}\text{Cl}_{10}$  and  $\text{LiCF}_3\text{CO}_2$ .

10. (Original) A lithium secondary battery according to claim 4, wherein the electrolytic salt is at least one of  $\text{LiPF}_6$ ,  $\text{LiN}(\text{CF}_3 \text{ SO}_2)_2$ ,  $\text{LiClO}_4$ ,  $\text{LiBF}_4$ ,  $\text{LiAsF}_6$ ,  $\text{LiI}$ ,  $\text{LiBr}$ ,  $\text{LiSCN}$ ,  $\text{Li}_2\text{B}_{10}\text{Cl}_{10}$  and  $\text{LiCF}_3\text{CO}_2$ .

11.-14. (Cancelled).

15. (Previously presented) A lithium secondary battery according to claim 3, wherein each of the compounds represented by the formula (2) and by the formula (3) has a molecular weight of 300-1000.

16. (Previously presented) A lithium secondary battery according to claim 3, wherein each of the compounds represented by the formula (2) and by the formula (3) has a molecular weight of 500-800.

17. (Previously presented) A lithium secondary battery according to claim 3, wherein the number of carbon atoms in AO is 1-4.

18. (Previously presented) A lithium secondary battery according to claim 3, wherein all of  $Z_4$ ,  $Z_5$  and  $Z_6$  are organic groups having an acryloyl group or a methacryloyl group.

19. (Previously presented) A lithium secondary battery according to claim 3, wherein p, q, r,  $\alpha$ ,  $\beta$  and  $\gamma$  are 1-3; and  $p+q+r$  and  $\alpha+\beta+\gamma$  are 3-9.

20. (Previously presented) A lithium secondary battery according to claim 4, wherein said molar ratio is 0.5 to 4.

21. (Previously presented) A lithium secondary battery according to claim 20, wherein said molar ratio is 1-2.5.

22. (Previously presented) A lithium secondary battery according to claim 3, wherein said polymerizable composition consists essentially of said boron-containing compound represented by the formula (2) and said boron-containing compound represented by the formula (3).

23. (Previously presented) A lithium secondary battery according to claim 3, wherein said polymerizable composition consists of said boron-containing compound represented by the formula (2) and said boron-containing compound represented by the formula (3).

24. (New) A lithium secondary battery according to claim 3, wherein the positive electrode contains a laminar lithium compound.